

(USA) **CreatorStar**

2 Side Coated Gloss

Property		Units	Tolerance	Text				Cover		
				60#	70#	80#	100#	80#	100#	130#
Substance	ISO 536	gsm	± 4%	89	104	118	148	216	270	351
Thickness	TAPPI 411 (100 KPa)	pt.	± 7%	2,64	3,19	3,62	4,53	7,01	9,02	11,22
Opacity	TAPPI 519	%	-2	90,0	91,5	94,5	96,0	98,5	99,0	99,7
Paper Gloss	TAPPI 480	%	± 5	66	67	68	70	70	70	70
Brightness	TAPPI 525	Index	± 2	96	96	96	96	96	96	96
Whiteness CIE D65 /10°	ISO 11475	Index	± 3	123	123	123	123	123	123	123
Relative Humidity	TAPPI 502	%	± 7	48	48	48	48	48	44	44

• Last updated: **19/08/2009**

• Values are subject to change without notice.

(USA) **CreatorSilk**

2 Side Coated Silk (Dull)

Property		Units	Tolerance	Text				Cover		
				60#	70#	80#	100#	80#	100#	130#
Substance	ISO 536	gsm	± 4%	89	104	118	148	216	270	351
Thickness	TAPPI 411 (100 KPa)	pt.	± 7%	3,07	3,50	3,94	5,00	7,09	9,57	13,39
Opacity	TAPPI 519	%	-2	91,0	92,5	94,2	97,0	98,9	99,3	99,6
Paper Gloss	TAPPI 480	%	± 5	30	30	30	30	35	35	35
Smoothness Bekk	ISO 5627	s	-100	300	300	300	250	250	200	70
Brightness	TAPPI 525	Index	± 2	96	96	96	96	96	96	96
Whiteness CIE D65 /10°	ISO 11475	Index	± 3	120	120	120	120	120	120	120
Relative Humidity	TAPPI 502	%	± 7	48	48	48	48	48	44	44

• Last updated: **19/08/2009**

• Values are subject to change without notice.