


Fortissimo C1S WhiteBack - Recycled



Caliper	Basis Weight	Substance	Stiffness Taber MD 15°	Stiffness Taber CD 15°	Brightness top C/2°	Brightness reverse C/2	Gloss 75°
PT	LBS	(g/m ²)	(mNm)	(mNm)	(%)	(%)	(%)
	24x36"	ISO 536	ISO 2493	ISO 2493	ISO 2470		ISO 8254
± 5 %		± 4 %	-15%	-15%	± 1,5%	± 1,5%	> 45
13.3	154	250	9.1	4.2	79.5	74.5	> 45
14.7	169	275	11.6	5.2	79.5	74.5	> 45
16	184	300	14.3	6.4	79.5	74.5	> 45
17.5	200	325	18.1	8.1	79.5	74.5	> 45
19	215	350	22.1	9.9	79.5	74.5	> 45
21	230	375	26.6	11.9	79,5	74.5	> 45
22	246	400	32	14.3	79.5	74.5	> 45
23	261	425	38	16.8	79.5	74.5	> 45
24	277	450	43.4	19	79.5	74.5	> 45

Test Conditions ISO 187 23°C / 50 % HR

9/13/2018