


# Fortissimo EB C1S GreyBack



Clay coating  
 White waste paper  
 Waste paper  
 Waste paper  
 Pigmenting

Caliper	Basis Weight	LBS/MSF	Substance	Stiffness Taber MD 15°	Stiffness Taber CD 15°	Brightness top C/2°	Gloss 75°
PT	LBS		(g/m <sup>2</sup> )	(mNm)	(mNm)	(%)	(%)
	24x36"		ISO 536	ISO 2493	ISO 2493	ISO 2470	ISO 8254
± 5 %			± 4 %	-15%	-15%	± 1,5%	> 45
11.0	141	47	230	5	1.9	79.5	> 45
11.8	148	49	240	5.3	2.1	79.5	> 45

Test conditions: ISO 187 23°C / 50% RH

9/13/2017

[www.mkdint.com](http://www.mkdint.com)