



Portland Offset Plus

Basis Weight	Basis size-25x38"	40.0	50.0	60.0	70.0	
Grammage, g/m ²	T410 om-98	60 ± 4%	74 ± 4%	89 ± 4%	104 ± 4%	
Caliper	PT	3	3.8	4.6	5.3	
Smoothness, sec/10ml	T479 om-91	25 ± 10	25 ± 10	25 ± 10	25 ± 10	
Brightness, %ISO (C/2°)	ISO 2470-1999	95 ± 1	95 ± 1	95 ± 1	95 ± 1	
Opacity, %	ISO 2471-1999	≥ 86	≥ 90	≥ 90	≥ 90	
Cobb Size 60", g/m ²	T441 om-98	30 ± 5	30 ± 10	30 ± 10	30 ± 10	
Stiffness, mN.m	T535 om-96	MD	≥ 0.12	≥ 0.26	≥ 0.40	≥ 0.70
		CD	≥ 0.06	≥ 0.13	≥ 0.20	≥ 0.35
Moisture, %	T412 om-94	5.0 ± 0.5	5.0 ± 0.5	5.0 ± 0.5	5.0 ± 0.5	