



## Stark Kraftback C1S

GSM	Basis Weight	Caliper	Stiffness Taber 15°		Stiffness L&W 5°	
TAPP14	24x36"		TAPPI 489		TAPPI 556	
g/m <sup>2</sup>	LBS	PT	mNxm		mNx m	
			CD	MD	CD	MD
180	111	11	2,7	5,5	5.3	10,7
200	123	12	3.9	7.8	7,6	15.2
225	138	14	5,3	10.6	10,3	20.7
245	151	16	6,4	12,8	12.5	25,0
260	160	17	7,7	15.4	15,0	30,0
275	169	18	9,3	18,6	18, 1	36,3
295	181	20	11.8	23,6	23.0	46,0
305	187	21	12.5	25.3	24.4	49,3
325	200	22	14,9	30,1	29,1	58,7
345	212	24	18.3	36,8	35,7	71,8
365	224	26	20.6	42,2	40,2	82,3
390	240	28	24.5	51,2	47,8	99,8
420	258	30	27.4	60.4	53.4	117.8

420 gsm is a special production

**Brightness: 81% Tappi 525/ISO 2470**

Smoothness: 1 PPS (um) Tappi 555

Cobb (1min) Top (g/m<sup>2</sup>) 25-45 Tappi 441

Cobb (2Min) Back (g/m<sup>2</sup>) 50-80 Tappi 441

Moisture: 6.5-9% Tappi 412

2019